

Combustion Characteristics of Briquettes Produced from Kurumthotti herbal and Jack fruit peel

M.Prabhu^{1*}, S.Sreenath², K.Gokul Raj³, P. Premkumar⁴

¹Assistant Professor, ^{2,3,4}UG Scholar

Department of Mechanical Engineering, JCT College of Engineering and Technology,
Coimbatore, India

Email id: Parumal.sami@gmail.com^{1*}

Article Received: 28 April 2025

Article Accepted: 29 April 2025

Article Published: 11 May 2025

Citation

M.Prabhu, S.Sreenath, K.Gokul Raj, P. Premkumar, "Combustion Characteristics of Briquettes Produced from Kurumthotti herbal and Jack fruit peel", Journal of Next Generation Technology (ISSN: 2583-021X), vol. 5, no. 3, pp. 42-51, 2025. DOI: [10.5281/zenodo.15706410](https://doi.org/10.5281/zenodo.15706410)

Abstract

Briquette density is the primary criterion used to assess briquette quality. From the standpoint of manipulation, burning rate, briquette longevity, etc., briquette density is crucial. The current study examines the physical and combustion properties of Kurumthotti herbal sticks and Jack fruit peel, including their length, diameter, mass, density, moisture content, total ash content, fixed carbon, volatile matter, and gross calorific values. Theoretical assessments of the variables that affect the quality of the briquettes were carried out throughout our investigation. The density and strength characteristics of the produced briquette were ascertained in order to assess its quality.

Keyword: *Moisture content, volatile matter, fixed carbon, Total Ash content, Gross Calorific Value.*

I. INTRODUCTION

It is impossible to overstate how crucial energy is to a country's prosperity. The reason for this is that energy is essential to both social and economic progress. Around the world, agriculture produces 140 billion metric tons of biomass annually. A staggering quantity of energy and raw materials, about equal to 50 billion tons of oil, may be produced from this volume of biomass. Agricultural biomass is waste that, if turned into energy, may replace fossil fuels in a sustainable manner, cut greenhouse gas emissions, and give renewable energy to the 1.6 billion people in developing nations who do not yet have access to electricity [4]. Remaining stalks, roots, leaves, husks, shells, and animal feeds are examples of biomass. Waste biomass is a plentiful renewable resource that is almost completely free. The briquetting process, which is defined as the compaction of residues into a product with a greater density than the original material, is one of these promising technologies, despite the fact that there are several conversion pathways by which these leftovers might be transformed into biomass energy [1]. Briquetting is another definition of it as a densification procedure. Briquette use may significantly lower the need for wood, which will lessen the amount of deforestation [3], [5]. Investigating the physical and combustion properties of briquettes

made from Kurumthotti herbal and Jack fruit peel using a piston press mechanism is the main goal of this work [2].

II. METHODOLOGY

The research methodology flow chart is shown below figure 1, showing how the study was conducted.




Figure 1. Flow chart of Research Methodology of the proposal work

A. Selection of Biomass:

There are many different kinds of trees and woodlands in the globe. Since we are just talking about woods here, each type of wood has unique qualities. Here, we've chosen the powdered Jack fruit[6]. Due to the high Lignin Property of Jack fruit. The Jack fruits's ability to bind and burn is enhanced by the lignine property [9]. Every Ayurvedic industrial company carries it. One kind of herbal waste is Kurumthotti herbal. This material weighs little and burns easily. Thus, Kurunthotti Materials is our choice [7]. The raw material of the Kurunthotti herbal and Jack fruit as shown in Figure 2..



Figure 2. Kurunthotti Herbal Waste and Jack fruit peel

B. Drying:

Pre-treatments could be necessary in order to maximize the product's calorific value and energy content before densification. Chop length/grinding; drying to the necessary moisture content; application of a binding agent are examples of pre-treatments. For each densification operation, a particular cut length and/or grinding are needed to accomplish: Reduced energy consumption during densification, denser goods and a reduction in the final product's breakage. Reduced moisture increases the fuel's durability and density. The ideal moisture content for most biomass densification procedures is between 8% and 20%. A tiny bit of moisture is needed for the majority of compaction procedures in order to "soften" the biomass for compaction. The strength and durability of the densified biomass are reduced above the ideal moisture content.

C. Addition of a Binding Agent:

Typically, sawdust helps the biomass's natural binder, lignin, bind the material together to create densified biomass known as briquettes. The natural binding agents in the material have an impact on the density and durability of densified biomass. The higher the protein and starch concentration, the greater the binding ability. The material may be given binding agents to improve its binding qualities. Binders such as vegetable oil, clay, starch, and cooking oil are frequently utilized [8]. Cassava starch is widely accessible on the market. Its potential to bond is excellent. Here, Cassava starch is utilized as a biomass binder [13], [21]. The Cassava starch binder is shown in Figure 3.



Figure 3. Cassava Starch Binder

D. Making of Briquette:

The Super-70 briquetting machine is specifically made for industries with medium levels of raw material availability and medium production requirements. This briquetting machine is specifically made using cutting-edge technology, which reduces the need for expensive monitoring [10]. If the size of the raw materials is less than 12 mm, we can grind them into a Super-70 briquetting machine instead of directly grinding them. The Setup and specification

of the Briquetting machine show in Figure 4. and Table 1. For the purpose of producing consistent briquettes from Kurunthotti herbs and Jack fruit peels generated in various mixed proportions, the dwell period of each press was maintained at 60 seconds [16]. The briquette die for biomass production is shown in Figure 5. 150 grams of Kurunthotti herbs and Jack fruit peels were weighed, and they were manually and thoroughly combined with the prepared binder solution to create a homogenous moist mass with a consistent size. In a variety of ratios, including 100:0 (S1), 20:80 (S2), 50:50 (S3), 20:80 (S4) and 0:100 (S5) [11], [12], [14], [20]. The Compositions of the Kurunthotti herbs and Jack fruit peels as illustrated in the Figure 6.



Figure 4. Briquette Machine Setup



Figure 5. Dye for Briquette

Table1 Specification of Briquetting machine

S.No	Model	Super 70
1.	R.P.M	240
2.	Power Requirements	49 HP
3.	Production Capacity	750 Kg/hr. [$\pm 20\%$ depending on density and quality of raw material]
4.	Finished Product Size	80 mm Diameter
5.	Finished Product Shape	Cylindrical
6.	Finished Product Length	70 mm to 30 mm
7.	Raw Material Form	Up to 4 mm size can be used directly




Figure 6. Samples of Kurunthotti herbs and Jack fruit peels

III. DETERMINATION PHYSICAL AND COMBUSTION CHARACTERISTICS:

Carefully examining every sample revealed the physical characteristics of the biomass briquettes, including Moisture content, Volatile matter, Ash content, Fixed content and Calorific Value [17], [18]. All five briquettes' heat energy values and proximate analyses were looked at by specialist testing services, using an approach compliant with ASTM standard E711-87(2004), [15]. The Proximity testing machine is shown in Figure 7. The R.B for briquette samples are shown in Table 2



Figure 7. The Proximity testing machine

Table 2 R.B for Briquette Samples:

PARAMETER	100:0	80:20	50:50	20:80	0:100
Moisture	5.74	4.7	6.23	5.28	7.7
Volatile matter	70.10	74.33	76.74	77.35	72.43
Ash	16.56	7.5	7.65	7.77	15.78
Fixed carbon	7.60	13.47	9.38	9.60	4.09
Calorific value	3475	4984	5018	5175	4345

IV. RESULT AND DISCUSSION:

The R.B. and the parameters (moisture content, volatile matter, ash content, and fixed carbon) for the briquette sample are displayed in Figure. 8., Figure 9, Figure 10, and Figure 11. Of all the samples, S2 (80:20) has the lowest moisture content, whereas S5 (0:100) has the highest moisture content. Even with less moisture, a significant calorific value is possible [19]. When compared to the other samples, the volatile concentration of the S4 (20:80) is greater. Higher heating values are possible if the percentage of volatile materials is more than 75%. The volatile matter content of Kurunthotti plants and Jack fruit peels is around 76% [24]. In comparison to all samples, the S2 has the lowest ash content if the ash concentration is less than 18% and has a good heating value [22]. Have an excellent calorific value if the fixed carbon content is less than 7.5%. Out of all the samples, the S5 had the least amount of fixed

carbon [25]. Figure 11 shows the R.B. and the Calorific Value for the briquette sample. A high value indicates that the briquette is an excellent biomass. of all the samples, the S4(20:80) has the highest calorific value [23].




Figure 8. R.B for Briquette sample Vs Moisture




Figure 9. R.B for Briquette sample Vs Moisture



Figure 10. R.B for Briquette sample Vs Ash




Figure 11. R.B for Briquette sample Vs Fixed Carbon




Figure 12. R.B for Briquette sample Vs Calorific Value

V. CONCLUSION

The investigation's findings have shown that, in addition S4 (20:80). As a result, there is a large burning capacity. S4 briquetted combination (20:80) has the potential to yield biomass fuels of superior grade. Premium briquettes have low total ash content, oil content, carbon content, and high calorific value. S1 (80:20) has a low calorific value and very low total ash content. After that, S2 has low total ash content and a very high calorific value. The briquettes S1 and S5 have high total ash content and low calorific values. There is a constant carbon content in S4 (20:80). Out of these four different briquettes, we have selected the S3 (50:50) briquetted sample. This is 80% efficient based on the Calorific Value of earlier samples. Future aims for this investigation include thermogravimetric analysis, differential scanning calorimetry (DSC) analysis, ultimate analysis, and an assessment of the strength-to-weight ratio.

References

- [1]. Sunday Yusuf Kpalo., Mohamad Faiz Zainuddin., Latifah Abd Manaf., & Ahmad Muhaimin Roslan. (2020). A Review of Technical and Economic Aspects of Biomass Briquetting, *Sustainability*, 12, 4609, 1-30.
- [2]. Katimbo A., Kiggundu N., Kizito S.; Kivumbi H.B., & Tumutegyereize P. (201). Potential of densification of mango waste and effect of binders on produced briquettes. *Agric. Eng. Int Cigr J.*16, 146–155.
- [3]. Maninder Kathuria R.S., & Grover S. (2012). Using Agricultural Residues as a Biomass Briquetting: An Alternative Source of Energy. *Iosr J. Electr Electron. Eng.*1, 11–15. [Cross Ref].
- [4]. Kumar,D., & Singh.B. (2017). Role of biomass supply chain management in sustainable bioenergy production. *Biofuels*. 1–11. [Cross Ref].
- [5]. Rahman M.A., Møller H.B., & Alam M.M. (2018). Assessing the energy potential of agricultural residues and an approach to meet the rural energy demand: The Bangladesh perspective. *Biomass Convers Biorefinery*. 8, 925–934. [Cross Ref].
- [6]. Kpalo, S.Y., Zainuddin M.F., Halim H.B.A., Ahmad A.F., & Abbas Z. (2019). Physical characterization of briquettes produced from paper pulp and Mesua ferrea mixtures. *Biofuels*, 1–8.
- [7]. Garrido M.A., Conesa J.A., & Garcia M.D. (2017). Characterization and production of fuel briquettes made from biomass and plastic wastes. *Energies*, 10, 1–12.
- [8]. Zhang G., Sun Y., & Xu Y. Review of briquette binders and briquetting mechanism. *Renew. Sustain. Energy Rev.*82, 477–487.
- [9]. Zhang X., Xu D., Xu Z., & Cheng. (2001). The effect of different treatment conditions on biomass binder preparation for lignite briquette. *Fuel Process Technol.* 73, 185–196.
- [10]. Manickam I.N., Ravindran D., & Subramanian P. (2006). Biomass densification methods and mechanism. *Cogener. Distrib. Gener J.* 21, 33–45.
- [11]. Antwi-Boasiako C., & Acheampong B.B. (2016). Strength properties and calorific values of sawdust-briquettes as wood-residue energy generation source from tropical hardwoods of different densities. *Biomass Bioenergy*. 85, 144–152.
- [12]. Mendoza-Martinez C.L., Sermyagina E., Carneiro O.A.D.C., Vakkilainen E., & Cardoso M. (2019). Production and characterization of coffee-pine wood residue briquettes as an alternative fuel for local firing systems in Brazil. *Biomass Bioenergy*, 123, 70–77.

- [13]. Borowski G., Stepniewski W., & Wójcik-Oliveira K. (2017). Effect of starch binder on charcoal briquette properties. *Int. Agrophysics*, 31, 571–574. [Cross Ref].
- [14]. Ujjinappa S., & Sreepathi L.K. (2018). Production and quality testing of fuel briquettes made from pongamia and tamarind shell. *Sadhana*, 43, 1–7. [Cross Ref].
- [15]. ASTM D 3175-18. (2018). Standard Test. Method for Volatile Matter in the Analysis Sample of Coal and Coke, *ASTM International: West Conshohocken, PA, USA*. [Cross Ref].
- [16]. Chin O.C., & Siddiqui K.M. (2000). Characteristics of some biomass briquettes prepared under modest die pressures. *Biomass Bioenergy*, 18, 223–238.
- [17]. Lubwama M., Yiga V.A.(2017). Development of ground nut shells and bagasses briquettes as sustainable fuel sources for domestic cooking applications in Uganda. *Renew. Energy*, 111, 532–542. [Cross Ref].
- [18]. Mandal S., Prasanna Kumar G.V., Bhattacharya T.K., Tanna H.R., & Jena P.C. (2019). Briquetting of Pine Needles (*Pinus roxburgii*) and Their Physical, Handling and Combustion Properties. *Waste Biomass Valorization*, 10, 2415–2424. [Cross Ref].
- [19]. Brožek M. (2016). The effect of moisture of the raw material on the properties briquettes for energy use. *Acta Univ Agric. Silv. Mendel. Brun*, 64, 1453–1458. [Cross Ref].
- [20]. Emerhi E.A.(2011). Physical and combustion properties of briquettes produced from sawdust of three hardwood species and different organic binders. *Adv. Appl. Sci. Res*, 2, 236–246.
- [21]. Sen R., Wiwatpanyaporn S., & Annachhatre A.P. (2016). Influence of binders on physical properties of fuel briquettes produced from cassava rhizome waste. *Int. J. Environ. Waste Manag*, 17, 158–175. [Cross Ref].
- [22]. ISO 18122. (2015). Solid Biofuels—Determination of Ash Content; *ISO: Geneva, Switzerland*.
- [23]. ISO 18125. (2017). Solid Biofuels—Determination of Calorific Value; *ISO: Geneva, Switzerland*.
- [24]. ISO 18123. (2015). Solid Biofuels—Determination of the Content of Volatile Matter; *ISO: Geneva, Switzerland*.
- [25]. ISO 16948. (2015). Solid Biofuels—Determination of Total Content of Carbon, Hydrogen and Nitrogen. *ISO: Geneva, Switzerland*.